

SPA-230 FR



SPECIFICATIONS	IMPERIAL	TEST METHOD
Material	100% polyester	DIN 60001,ASTM D7641
Weight	230g/sq.m,6.8oz/sq.yd	ISO536
Yarn	75×75 denier	DIN EN ISO 2060,ASTM D 1907
Weave Method	Warp-knitted 2 bar	
Shrinkage	≤2 %	200 °C,45s
Opacity	>80%	ISO2471
Elasticity	10~15%	"Length*Width=200*50mm,
Flame Resistance	DIN 4102-1-B1,NFPA 701	Speed=100mm/min,Tension=20N"
Recommend Fixation Temperature	190-200 °C,45s	DIN 4102-1-B1,NFPA 701 Test 1
Yellowing Temperature	≥210 °C	
Maximum Width	3.2m	SUPRKC REX-C400,30s
Standard Length	100m	DIN EN ISO 3759, ASTM D751-2006
Compatible Inks	Dye-sub Transfer,Dye-sub Direct,Latex	
Application	Pop-up,Geometric,Tradeshaw,Grandformat	